





20YPTD

50Hz交流B-P性能数据/A.C. Core loss curves properties at 50Hz

磁感强度 B (T)	铁损 P (W/kg)	磁感强度 B (T)	铁损 P (W/kg)
0.45	0.052	1.61	0.656
0.50	0.064	1.62	0.668
0.55	0.076	1.63	0.680
0.60	0.090	1.64	0.693
0.65	0.104	1.65	0.706
0.70	0.119	1.66	0.719
0.75	0.136	1.67	0.733
0.80	0.154	1.68	0.748
0.85	0.173	1.69	0.763
0.90	0.193	1.70	0.779
0.95	0.215	1.71	0.796
1.00	0.238	1.72	0.814
1.05	0.262	1.73	0.832
1.10	0.288	1.74	0.852
1.15	0.314	1.75	0.873
1.20	0.341	1.76	0.895
1.25	0.370	1.77	0.919
1.30	0.400	1.78	0.944
1.35	0.432	1.79	0.972
1.40	0.467	1.80	1.002
1.45	0.505	1.82	1.070
1.50	0.546	1.85	1.168
1.55	0.592	1.87	1.244
1.60	0.645	1.90	1.382